

Z25 COLORSHADE

Technical Specifications

FABRIC MASS RANGE	grams per square metre	190-200 gsm
TYPICAL BURST STRENGTH RANGE	(SABS 1703:2003)	240-270 kPa
MINIMUM SPECIFIED BURST RATIO	kPa per gram of fabric (SABS 1703:2003)	1.20
MEAN BURST RATIO	kPa per gram of fabric	1.35
TYPICAL BURST STRENGTH RANGE	(AS 2001.2.4-1990 method B)	2100-2500 kPa
BURST FORCE 25.4 STEEL BALL	(AS 2001.2.19-1988)	1200 N
MEAN BREAK STRENGTH - WEFT	(AS 2001.2.3.1-2001)	900 N
MEAN BREAK STRENGTH - WARP	(AS 2001.2.3.1-2001)	450 N
WIND TUNNEL TESTS	conducted by CSIR (SA) (max capability of LSWT)	>200 km/hour
LIMITED WARRANTY AGAINST UV DEGRADATION		10 years

Standard 50m Stentered Rolls - Cut lengths on request